



**profiltra**  
customized solutions



**PIGMENTS FOR PAINTS AND COATINGS**



## PAINT

Our portfolio consists of below mentioned organic pigments for the paint industry.

Color Index No.	Heat Stability (°C)	Light Fastness	Acid Resistance	Alcohol Resistance	Alkali Resistance	Oil Resistance	Water Resistance	Liquid decorative / architectural paints	Liquid industrial coatings	Powder coatings	Coil Coatings	Auto Refinish	Auto OEM
<b>PB 15:1</b>	200	8	5	5	5	4 - 5	5	m	l	l			
<b>PB 15:2</b>	200	8	5	4 - 5	5	5	5	m	s	m			
<b>PB 15:3</b>	200	8	5	5	5	5	5	m	m	m	m	s	
<b>PB 15:4</b>	200	8	5	5	5	5	5	m	m	m	s	s	
<b>PG 7</b>	200	8	5	5	5	5	5	m	m	m	s	s	
<b>PO 5</b>	160	6	5	3	5	4	5	m	l				
<b>PO 34</b>	200	6 - 7	5	5	5	4 - 5	5	m	m	m	l		
<b>PO 36</b>	160	8	5	5	5	5	5	m	m	m	s	m	s
<b>PO 43</b>	200	6	5	5	5	5	5	m	s	m	s	s	l
<b>PR 112</b>	180	7 - 8	5	4 - 5	5	4	5	m	s				
<b>PR 122</b>	200	8	5	5	5	5	5	m	m	m	m	m	s
<b>PR 146</b>	180	5 - 6	5	4 - 5	5	5	5	s	s				
<b>PR 170</b>	160	7	5	4 - 5	5	5	5	m	m	s		l	
<b>PR 254</b>	200	8	5	4	5	5	5		m	m	m	m	m
<b>PV 19</b>	200	7 - 8	5	5	5	5	5	m	m	m	m	m	s
<b>PV 23</b>	160	7 - 8	5	4	5	5	5	m	m	m	m	m	s
<b>PY 74</b>	140	7 - 8	5	3 - 4	5	4	5	m	s				
<b>PY 83</b>	200	7 - 8	5	4 - 5	5	5	5	m	m	s			
<b>PY 139</b>	200	8	5	5	5	5	5	m	m	m	s	s	s
<b>PY 151</b>	200	8	5	4 - 5	3	5	5	l	m	m	l	m	l
<b>PY 154</b>	200	8	5	5	5	5	5	m	m	m	l	m	s
<b>PY 194</b>	200	8	5	4	5	4 - 5	5	m	m	m	l	l	

Heat stability: 30 minutes baking time  
 Light fastness: tested in accordance to DIN EN ISO 105-B01  
 Resistance to solvent: tested in accordance to DIN EN ISO 105-A02  
 Resistance to oil: tested in accordance to DIN EN 20105-A03

m = main application  
 s = suitable  
 l = limited suitable